

NCV95 - Polyester fleece (LF)





Characteristics

NCV95 is a fine, **cabonized polyester fleece** for the shielding of low-frequency electric fields (LF).

Application

In the **interior** for walls, ceilings and floors as **intermediate layer**, in **drywall constructions** or for loose layings. Further together with our grounding plug EST as a **cheap "earthed mattress pad"**.

Technical data

- Width: 95 cm
- Length: By the meter / 20 m roll
- Attenuation: 40 dB (99 %)
- Weight: 90 g/m²
- Material thickness: 0.55 mm
- Color: Black
- Tensile strength: 260 N/mm in longitudinal direction, 35 N/ mm in transverse direction
- Materials: Polyester, carbon coating
- Surface conductivity: 1000 ohm (square resistance R□)

Processing

In case of processing NCV95 as an intermediate layer we recommend using our dispersion glue DKL90 for adhesion. The wall and the backside of NCV95 should be coated with a paint roller. Insert the material wet on wet. Fix it manually (with disposable gloves) and press a gummed roller against the fleece to get a crease-free surface. Work guickly and strip by strip only so that the DKL90 glue does not dry. A crease-free adhesion is only possible on perfectly level surfaces! Structured surfaces (ingrain wallpaper, textured plastering) have to be smoothed. If that is not possible, we recommend using our shielding paint NSF34. Used as "earthed mattress pad", NCV95 has to be grounded from an electrician with our grounding plug EST.

Grounding

Due to the highly conductive surface this material can be contacted and grounded easily to shield low frequency (LF) electric fields.

Screening attenuation

The screening attenuation is regularly tested in our own EMC laboratory. We have measurement setups due to the following standards: ASTM D4935-10, IEEE Std 299-2006, IEEEE Std 1128-1998, ASTM A698/A698M-07. Please find the test report at our homepage directly on the product page.